

DG12-230(12V230Ah)



Specification



DG (Deep Cycle GEL) series is pure GEL battery with 15 years floating design life , it is ideal for standby or frequent cyclic discharge applications under extreme environments. By using strong grids, high purity lead and patented GEL electrolyte, the DG series offers excellent recovery capability after deep discharge under frequent cyclic discharge use, and it can offers 2 times cyclic life than the standard series. It is suitable for solar & wind system, marine, deep discharge UPS etc.



ISO 9001



ISO 14001



ISO 45001




MH 28539



BSTXD210316008519EC

Cells Per Unit	6
Voltage Per Unit	12V
Capacity	230Ah@10hour-rate to 1.80V per cell @25°C
Weight	Approx. 72.0 Kg (Tolerance ±5%)
Internal Resistance	≤6.5 mΩ (Full Charge Condition @25°C)
Terminal	DDefault F14(M8), L6 Optional
Max. Discharge Current	2300A (5 sec)
Design Life	15 years
Max. Charging Current	46.0 A
Reference Capacity	C3 172.5Ah C5 195.5Ah C10 230.0Ah C20 248.0Ah
Float Charging Voltage	13.38 V~13.50 V @ 25°C Temperature Compensation: -3mV/°C/Cell
Cycle Use Voltage	14.20 V~14.40 V @ 25°C Temperature Compensation: -4mV/°C/Cell
Operating Temperature Range	Discharge: -40°C~60°C Charge: 0°C~50°C Storage: -40°C~60°C
Normal Operating Temperature Range	25°C ±5°C
Self Discharge	RITAR Valve Regulated Lead Acid (VRLA) GEL batteries can be stored for up to 6 months at 25°C and then recharging is recommended. Monthly Self-discharge ratio is less than 2% at 25°C. Please charged batteries before using.
Container Material	A.B.S. UL94-HB, UL94-V0 Optional.

Dimensions



Constant Current Discharge Characteristics : A(25°C)

F.V/Time	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	399.0	333.5	222.3	136.7	89.2	67.4	51.5	41.8	30.0	23.9	13.1
1.65V	384.5	325.7	217.9	135.1	86.1	64.6	50.4	40.9	29.2	23.7	12.9
1.70V	353.9	300.3	205.3	132.6	84.8	63.0	49.2	40.3	28.3	23.5	12.7
1.75V	312.6	267.4	184.7	121.9	80.1	59.8	47.6	39.8	27.8	23.2	12.4
1.80V	276.7	238.0	168.2	115.0	76.3	57.5	45.8	39.1	27.4	23.0	12.2
1.85V	235.4	207.3	151.5	106.2	72.1	54.7	44.6	36.8	26.0	22.3	11.5

Constant Power Discharge Characteristics : W/Cell (25°C)


F.V/Time	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	681.7	585.9	412.1	257.0	169.1	128.7	98.9	80.6	58.5	47.0	25.8
1.65V	661.4	575.3	399.1	255.7	164.0	124.2	97.1	79.2	57.1	46.6	25.4
1.70V	627.5	543.4	380.6	252.1	162.4	121.4	95.2	78.1	55.6	46.2	25.0
1.75V	564.2	491.0	345.9	233.2	154.1	115.7	92.5	77.5	54.7	45.8	24.6
1.80V	508.2	443.1	318.2	221.3	147.6	111.7	89.2	76.4	53.9	45.4	24.1
1.85V	440.0	391.5	289.5	205.7	140.2	106.8	87.3	72.2	51.3	44.2	22.8

(Note) The above characteristics data are average values obtained within three charge/discharge cycle not the minimum values.
The battery must be fully charged before the capacity test. The C₁₀ should reach 95% after the first cycle and 100% after the third cycle.


DG12-230(12V230Ah)




Discharge Characteristics Curve




Charge Characteristic Curve for Cycle Use(IUU)




Cycle Life in Relation to Depth of Discharge




Relationship Between Charging Voltage and Temperature




Temperature Effects on Capacity




Storage Characteristics



Effect of Temperature on Long Term Life



Relationship of OCV And State of Charge(20°C)



(Note) All above information shall be changed without prior notice, RITAR reserves the right to explain and update the latest information.

HENGYANG RITAR POWER CO.,LTD.
RITAR POWER (VIETNAM) CO.,LTD.
 URL: www.ritarpower.com

Add: 10th Floor, Tower C, 1st Building, Software Industry Base, No.81, Xuefu Road, Nanshan District, Shenzhen, Guangdong, China 518057
 Tel: +86-755-33981668/83475380 Fax: +86-755-83475180 E-mail: magwang@ritarpower.com Version 25A-1-B